



DESCRIPTION

TAG VAPOR 95 is engineered for reducing concrete surface moisture, pH, surface porosity and to enhance adhesive bond performance. TAG VAPOR 95 is solvent free and dries quickly. Resulting in a quick return to service for remodel and new construction.



pH
7-12



Dry Time
Up to 60 mins



RH
Up to 95%



Adhesive Application
Immediate when dry

Limitations

**TAG VAPOR 95
PH REDUCER**

- Not for use to encapsulate asbestos
- Not for use when moisture exceeds 3.5% per ASTM F2659, or Relative Humidity of the concrete substrate exceeds 95% (ASTM F2170)
- Not for use where hydrostatic pressure exists
- Do not use if substrate pH is greater than 12.0 or below 7.0
- Concrete substrate must be a minimum of 5° F above dew point
- Ambient conditions must be between 60°-90° F - 30-65% RH
- Extreme ambient condition changes will affect the performance quality of the installation
- Do not install over chemically abated substrates
- Do not install over adhesive residue or cutback adhesive
- Do not allow product to freeze
- Do not use with dimensionally unstable floor coverings
- Do not use over concrete substrates which have been treated with silicates, either topically or entrained
- Do not use TAG VAPOR 95 with any other primers or sealers

Suitable Substrates

- Concrete substrates (at least 28 days old)
- On, above or below grade porous concrete installations
- Cement-based self-levelers/patching compounds
- Lightweight concrete

Substrate Requirements

- RH: 95% [ASTM F2170]
- pH: Between 7.0-12.0 [ASTM F710]

**PLEASE CONSULT TAG ADHESIVES'
TECHNICAL DEPARTMENT FOR SUBSTRATES
NOT LISTED AT 682-704-7547**

Surface Preparation

**TAG VAPOR 95
PH REDUCER**

FOLLOW ALL FLOOR COVERING MANUFACTURERS GUIDELINES. SUBSTRATES MUST BE PREPARED IN ACCORDANCE WITH ASTM F710 AS WELL AS THE FOLLOWING:

- Substrates must be dry, smooth, solid, structurally sound and flat.
- Substrates should be clean and free of dust, dirt, oil, grease, paint, curing agents or concrete sealers; topically applied or entrained, loosely bonded toppings, adhesive residue, loose particles, and any other substance that may prevent or reduce primer adhesion.
- Fill all surface cracks, grooves, depressions and non-moving joints with moisture resistance patching or self-leveling compounds.
- Substrate, adhesive and floor covering must be acclimated with HVAC in operation for 48 hours prior, during, and continuously after installation is complete.
- Ambient conditions, temperature must be between 60°-90° F and relative humidity must be between 30-65% during and following installation.
- When installing over radiant heated substrates, heat should be turned off 24 hours before, during, and after installation. When turning radiant heat back on, do so in 5° increments per hour to desired temperature. Floor temperature should not exceed 85° F.

Installation Instructions

Follow flooring manufacturer's guidelines for layout, design, and any special precautions for installation.

DISCLAIMER: FOLLOW THESE INSTRUCTIONS COMPLETELY OR DO NOT USE THIS PRODUCT.

- 1))*** If unfamiliar with a product, always perform a bond test. Spread a small area of sealer and install the desired floor covering into the adhesive to ensure the desired bond is achieved. ***
- 2) After surface preparation, apply sealer using the determined application method.

SUBSTRATE APPLICATION

- Apply an even coat of TAG VAPOR 95 with a 3/8" nap roller to the desired substrate. Allow TAG VAPOR 95 to dry to the touch. Only one coat is required for most applications
- Drying time: Will vary depending on ambient conditions and porosity of the substrate. .

NOTE: Foot traffic and adhesive application are typically allowed immediately after drying, depending on ambient jobsite conditions and porosity of the substrate.

Required Applications & Coverage

TAG VAPOR 95
PH REDUCER

Primer Application	Trowel Recommendation	Estimated Coverage
All Substrates	3/8" Nap Roller or Sprayer Applied	Up to 400 sqft/gallon

**** It is up to the end user to determine the application method, coverage rate and coats required.****

Cleanup

- While wet, use a cloth and soapy water to remove wet sealer
- When sealer is dry, use denatured alcohol or appropriate adhesive remover

Storage

- This product should be stored at temperatures between 50°-100° degrees F.
- This product has a shelf life of 2 years

Disclaimer: Users should determine the suitability of this information and product for their own purpose or application. The manufacturer is not responsible for the misuse of this product. ONLY TAG ADHESIVES ARE WARRANTED FOR USE WITH THIS PRODUCT. This product is a moisture reducer and may not perform above the stated moisture and pH limitations and is only warranted to maintain an adhesive bond when used over substrates specified in this document or as prescribed by TAG Adhesives. ASTM 2659 impedance readings that exceed 3.5 % may void the warranty.

Exclusively made by Lighthouse Adhesives



PROFESSIONAL FLOORING SUPPLY

PO Box 7558, Fort Worth, TX 76111
800-772-2706 | www.accesspfs.com

PROFESSIONALFLOORING
SUPPLY